

SECTION 03150 — WATERSTOPS FOR CONCRETE JOINTS

******* MasterFormat™ 2004 — Section 03 15 13 *******

PART 1 - GENERAL

1.01 SUMMARY

- a. Provide Adeka Corporation non-bentonite hydrophilic rubber waterstop where shown or specified for the following applications (provided by OCM, Inc. Chicago, IL):

Sealing cold joints and construction joints between structural elements against penetration of water from wet-face of structure.

Sealing piping penetrations against water penetration from wet-face of structure

1.03 SUBMITTALS

- a. Comply with pertinent provisions of Section 01340.
- b. Product Data: Within 15 calendar days after the contractor has received the owners notice to proceed, submit:
 1. Materials list of items proposed to be provided under this section.
 2. Manufacturer's specifications and other data needed to prove compliance with the specified requirements.
 3. Show drawings in sufficient detail to show fabrication, installation, anchorage, and interface of the work of this section with the work of adjacent work.
 4. Manufacturer's recommended installation procedures which, when approved by the architect, will become the basis for accepting or rejecting actual installation procedures used on the work.

1.04 DELIVERY, STORAGE & HANDLING

- a. Delivery & storage:
 1. Deliver materials to job site in manufacturer's unpacked containers with all labels intact and legible at time of use.
 2. Maintain products in a dry condition during delivery, storage, handling, installation and concealment.
- b. Comply with pertinent provisions of Section 01620.

PART 2 – PRODUCTS

2.01 MANUFACTURER

Provide products manufactured by Adeka Corporation. Supplied by OCM, Inc. Chicago, IL Phone 800.999.3959 - International number 303.904.4624
www.adeka.com

2.01 WATERSTOP MATERIALS

1. KBA-1510FP use when wall/slab thickness greater than 4.0". Minimum 1" concrete coverage from edge of waterstop to surface of concrete wall/slab. Can be placed on waterside of rebar. Use in piping penetration when pipe diameter exceeds 2".

The product shall be a 15 mm X 10 mm flexible hydrophilic sponge rubber strip composed of vulcanized rubber and urethane polymer as the hydrophilic agent. The product shall not produce more than 0.03MPa expansion pressure when fully hydrated. and shall meet the minimum performance requirements as shown in the official literature (www.adeka.com).

Physical properties of the swelling rubber waterstop KBA-1510FP material:

PHYSICAL PROPERTIES	Adeka KBA-1510FP
Hardness	HsC 22
Tensile Strength (MPa)	0.8
Elongation (%)	350
Specific Gravity	0.60
Vulcanization	yes
Volume Expansion (%)	30
General Physical Properties	Vulcanized rubber, follows compression pressure

Physical properties of the gun grade swelling rubber waterstop (Adeka P-201):

PHYSICAL PROPERTIES	GUN GRADE
Hardness	A45
Tensile Strength (MPa)	4
Elongation (%)	850
Specific Gravity	1.25
Volume Expansion (%)	100
Restorability	Excellent

PART 3 – EXECUTION

3.01 EXAMINATION AND PREPARATION

Ensure rebar does not interfere with proper position of waterstop
Protect Waterstops during progress of work.
Clean joints of dirt and debris.

3.03 INSTALLATION

SMOOTH DRY CONCRETE

1. Surface of the concrete must be clean dry, clean and free of oil, dust and laitance
2. Paint concrete and hydrophilic waterstop strip with appropriate adhesive (3M-2141, Bostik 1142, Scotch Grip 1357, 3M Spray Adhesive or equal). Allow adhesive to become tacky - firmly press hydrophilic strip waterstop onto adhesive.
3. Place concrete without displacing or disturbing the position of the waterstop.

The expanding rubber waterstop is placed as shown on the Drawings. The expanding water stop must be placed no closer than 1 inches from the edge of the concrete pour to ensure it will not spall the concrete edge. The expanding rubber waterstop ends are placed with a parallel side by side bypass. A good and uniform contact of the strip to the concrete surface is of the utmost importance.

ROUGH CONCRETE - (hydrophilic strip does not have intimate contact with the concrete surface along the entire length of the strip)

1. Surface of the concrete must be clean dry, clean and free of oil, dust and laitance

Place a small bead of hydrophilic Adeka P-201 paste on the concrete. Press the hydrophilic strip waterstop onto the bead of P-201. Press firmly. Place nail or screw every 10~12 inches.

Check for any gaps between the product and the substrate. If gaps are present, fill in using appropriate gun grade hydrophilic material applied to the side of the strip.

2. Place concrete without displacing or disturbing the position of the waterstop.

END OF SECTION